


## 四层 (铜厚: 内层0.5oz/外层1oz)


 <p>四层板压合结构图</p>	铜厚:	H	0.0175	mm
	PP胶:	2116-RC54	0.11	mm
	芯板:	含铜	0.50	mm
	PP胶:	2116-RC54	0.11	mm
	铜厚:	H	0.0175	mm
	压合厚度:	0.75	±0.10	mm
	成品厚度:	0.85	±0.10	mm

 <p>四层板压合结构图</p>	铜厚:	H	0.0175	mm
	PP胶:	2116-RC54	0.11	mm
	芯板:	含铜	0.70	mm
	PP胶:	2116-RC54	0.11	mm
	铜厚:	H	0.0175	mm
	压合厚度:	0.95	±0.10	mm
	成品厚度:	1.05	±0.10	mm

 <p>四层板压合结构图</p>	铜厚:	H	0.0175	mm
	PP胶:	7628-RC46	0.185	mm
	芯板:	含铜	0.70	mm
	PP胶:	7628-RC46	0.185	mm
	铜厚:	H	0.0175	mm
	压合厚度:	1.10	±0.10	mm
	成品厚度:	1.20	±0.10	mm

 <p>四层板压合结构图</p>	铜厚:	H	0.0175	mm
	PP胶:	7628-RC46	0.185	mm
	芯板:	含铜	1.10	mm
	PP胶:	7628-RC46	0.185	mm
	铜厚:	H	0.0175	mm
	压合厚度:	1.50	±0.13	mm
	成品厚度:	1.60	±0.13	mm

 <p>四层板压合结构图</p>	铜厚:	H	0.0175	mm
	PP胶:	7628-RC46	0.185	mm
	芯板:	含铜	1.50	mm
	PP胶:	7628-RC46	0.185	mm
	铜厚:	H	0.0175	mm
	压合厚度:	1.90	±0.20	mm
	成品厚度:	2.00	±0.20	mm

 <p>四层板压合结构图</p>	铜厚:	H	0.0175	mm
	PP胶:	2116(RC58)	0.125	mm
	芯板:	含铜	2.00	mm
	PP胶:	2116(RC58)	0.125	mm
	铜厚:	H	0.0175	mm
	压合厚度:	2.27	±0.20	mm
	成品厚度:	2.40	±0.20	mm